

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>A61F 2/24</b>	<b>A2</b>	<b>(11) International Publication Number:</b> <b>WO 00/30567</b> <b>(43) International Publication Date:</b> 2 June 2000 (02.06.00)
<b>(21) International Application Number:</b> PCT/US99/27272 <b>(22) International Filing Date:</b> 16 November 1999 (16.11.99) <b>(30) Priority Data:</b> 09/197,808 23 November 1998 (23.11.98) US <b>(71) Applicant:</b> HEALTHSHIELD TECHNOLOGIES LLC [US/US]; Suite 201, 67 Prospect Avenue, West Hartford, CT 06106 (US). <b>(72) Inventors:</b> HOLLEY, Steven; 24 Bigelow Street, Brighton, MA 02135 (US). BARRY, John, E.; 18 Drake Lane, Derry, NH 03038 (US). TROGOLO, Jeffrey, A.; 228 Commonwealth Avenue, Boston, MA 02116 (US). <b>(74) Agents:</b> GOGORIS, Adda, C. et al.; Darby & Darby P.C., 805 Third Avenue, New York, NY 10022-7513 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>Without international search report and to be republished upon receipt of that report.</i>
<b>(54) Title:</b> ANTIMICROBIAL SUTURING RING FOR HEART VALVE  <b>(57) Abstract</b>  A suturing ring to attach the body of an implantable heart valve to heart tissue by sutures is composed of a fabric containing an inorganic antimicrobial agent. The fabric can have a material coating the fibers of the fabric in which particles of the agent are embedded. The coating material can be elastomeric and the fabric porous, to improve its flexibility, or non-porous and the fabric ring can be coated with a tissue compatible substance such as collagen. One type of ring has an annular top part to fit over one of top and bottom surfaces of the valve body and defining an opening to the heart valve, a step wall depending from the annular top part to extend along said valve body wall and an outwardly extending flange through which the sutures are to be sewn.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## ANTIMICROBIAL SUTURING RING FOR HEART VALVE

Modern implantable prosthetic heart valves are typically formed of an annular valve seat in a relatively rigid valve body. One or more valve members, such as spheres, disks or leaflets, are movable between a closed, seated position in the annular valve seat and an open position over a prescribed range of motion. Such mechanical heart valves are typically formed of blood compatible, non-thrombogenic materials, typically currently comprising pyrolytic carbon and titanium. The rigid valve body is formed of a biocompatible material, such as a suitable metal or plastic. Valves made of human and porcine tissue also have been developed.

Some types of heart valves utilize a suturing ring surrounding the valve body. The ring is to be sewn by the surgeon to the peripheral tissue of a natural heart valve orifice (the "the valve rim") after surgical removal of damaged or diseased natural valve structure. The suturing ring is made of a fabric or other similar material which can be penetrated by the needle used by the surgeon to fasten the valve body to the heart tissue. In some cases, the suturing ring includes a part to which the fabric is fastened so that the ring can be rotated relative to the heart valve body. Such an arrangement is shown in U.S. patent 5,766,240.

Brief Description of the Invention

The present invention relates to a suturing ring for a heart valve body containing an inorganic antimicrobial agent. In a preferred embodiment the ring is of fabric material. The antimicrobial properties of such a suturing ring has advantages in that it is able to kill certain types of bacteria which are present in the body and which, at least in the initial stages of implantation of the heart valve, can have adverse effects relative to infection and rejection of the valve and also its

proper operation. The antimicrobial fabric of the suturing ring of the invention is biocompatible, and presents no problem relative to its suturing by the surgeon. In a preferred embodiment of the invention, the antimicrobial agent is a zeolite.

5 The antimicrobial fabric for the suturing ring can be of a porous flexible material to accommodate heart movement or of a fabric that is fully coated with the antimicrobial agent. In either case, the fabric can be coated with a tissue compatible substance such as collagen.

10 The invention also provides a novel suturing ring having fabric material with an inorganic antimicrobial with the ring being rotatable relative to the heart valve body to permit its positioning relative to the heart tissue orifice.

#### Objects of the Invention

It is therefore an object of the invention to provide a heart valve suturing ring including a fabric containing an inorganic antimicrobial agent

15 Another object is to provide a suturing ring for a heart valve of porous fabric containing an inorganic antimicrobial agent.

An additional object is to provide a fabric suturing ring for a heart valve containing an inorganic antimicrobial agent which is coated by a tissue compatible substance.

20 Still a further object is provide a suturing ring for a heart valve having a fabric containing an inorganic antimicrobial agent which is rotatable relative to the heart valve body.

#### Brief Description of the Drawings

25 Other objects and advantages of the present invention will become more apparent upon reference to the following specification and annexed drawings in which:

Fig. 1 is a perspective view of a base fabric;

Fig. 2 is a cross-sectional view along lines 2-2 of Fig.1  
30 showing application of the coating material to the fabric;

Fig. 3 is a cross-sectional view of the fabric after the antimicrobial agent has been applied;

Fig. 4 is a cross-sectional view of the finished fabric after drying;

Fig. 5 is a perspective view of a heart valve fabric suturing ring according to the invention and Fig. 5A is a cross-section thereof;

Fig. 6 is perspective view of a rotatable collar for a suturing ring and

Fig. 6A is a cross sectional view showing the fabric of the invention applied.

#### Detailed Description of the Invention

All patents, patent applications, and publications listed herein are hereby incorporated by reference in their entireties.

Various types of fabrics containing the antimicrobial agent suitable for use as the suturing ring are first described.

1. Porous Fabric - Figs. 1-4 show an embodiment of the invention for processing a fabric that is porous and flexible to be used for the suturing ring.

Referring to Fig. 1, there is shown a base material comprising a piece of fabric 10 of the mesh type formed by fibers 12 which are laid transverse to each other and which define spaces, or pores, 14 between the fibers. The fibers can be of any suitable material, for example, cotton, nylon polyester, Teflon, e-PTFE and blends of these materials. For the suturing ring application, Teflon or polyester is preferred. The fabric can be either of the woven or non-woven type. The fabric 10 is shown by the arrows T as being able to be held under tension in both directions generally along the fabric length and width by any suitable mechanism (not shown), for example, rollers, clamps, etc.

Fig. 2 shows the fabric piece 10 in the stage of having a coating of an adherent material 18 applied to one surface. It should be understood that the invention is applicable to performing the process on both fabric surfaces and on the sides which form the pores 14. The adherent coating material 18 is a biologically compatible material such as, for example, acrylic, polyurethane, silicone, latex, polyglycolic lactic acid or other biodegradable polymer, especially one that is a hydrophilic, non-degrading polymer such as a hydrophilic polyurethane, for example TECOPHILIC which is made by Thermedics. These materials all have elastomeric properties.

In a preferred embodiment of the invention, the fabric coating material

18 is applied as a mixture of a high strength RTV dispersed in a solvent, such as xylene. A preferred composition of the mixture is 50% RTV and 50% xylene although the ratio of the two materials can be varied. Increasing the proportion of the coating material in the mixture makes the final product less pliable.

5 In a preferred manner of application of the coating material 18, the fabric 10 is held under tension in its lengthwise dimension. The coating material-solvent mixture is supplied by a peristaltic pump to an ultrasonic disperser. The ultrasonic disperser creates a fine mist of the mixture that is blown out of the disperser by an air source, illustratively shown by reference numeral 19, to coat the  
10 fabric 10. There can be one or more dispersers and air sources on both sides of the fabric and at varying angles to fully coat the entire surfaces of the fabric fibers. Alternatively, only one surface is coated, the two surfaces are coated sequentially, or both surfaces coated at the same time. In the application for the suturing ring the fabric is coated on both surfaces.

15 Fig. 3 shows the fabric 10 having been coated on one side with the coating material mixture. As seen, the coating material 18 extends into the openings 14 between the fibers of the fabric and also coats the top of each of the fibers. There is a continuous layer of the coating material 18 over the fabric at this stage of the process, that is, the coating material fills the pores 14. The fabric can  
20 be cycled relative to the disperser as many times as needed. That is, the deposition of the coating material mixture on the fabric can be accomplished by applying a desired number of layers to achieve a desired thickness. The layers are contiguous to and mixed with each other. The depth of the coating material 18 on top of the fabric is selected to be between 0.01 and 50 microns, more preferably  
25 between 0.1 and 25 microns, and most preferably between 0.1 and 10 microns.

As is also shown in Fig. 3, an inorganic antimicrobial agent 20 in powdered form is applied to the coating material 18 while it is still wet. During this step the fabric preferably is held under tension in both directions, that is, generally  
30 along both the fabric fibers' cross-direction. The powdered antimicrobial agent 20 becomes immersed into and bonds with the coating material layer 18 on the fabric. The xylene evaporates from the coating.

As to the inorganic antimicrobial agent 20, a number of metal ions,

which are inorganic materials, have been shown to possess antibiotic activity, including silver, copper, zinc, mercury, tin, lead, bismuth, cadmium, chromium and thallium ions. These antibiotic metal ions are believed to exert their effects by disrupting respiration and electron transport systems upon absorption into bacterial or fungal cells. Antimicrobial metal ions of silver, gold, copper and zinc, in particular, are considered safe even for *in vivo* use. Antimicrobial silver ions are particularly useful for *in vivo* use due to the fact that they are not substantially absorbed into the body. That is, if such materials are used for the antimicrobial fabric, they should pose no hazard to the body.

Antibiotic zeolites also are suitable as the agent. These have been prepared by replacing all or part of the ion-exchangeable ions in zeolite with ammonium ions and antibiotic metal ions, as described in U.S. Patent Nos. 4,938,958 and 4,911,898. Such zeolites have been incorporated in antibiotic resins (as shown in U.S. Patent Nos. 4,938,955 and 4,906,464) and polymer articles (U.S. Patent No. 4,775,585). Polymers including the antibiotic zeolites have been used to make refrigerators, dish washers, rice cookers, plastic film, chopping boards, vacuum bottles, plastic pails, and garbage containers. Other materials in which antibiotic zeolites have been incorporated include flooring, wall paper, cloth, paint, napkins, plastic automobile parts, catheters, bicycles, pens, toys, sand, and concrete. Examples of such uses are described in U.S. Patents 5,714,445; 5,697,203; 5,562,872; 5,180,585; 5,714,430; and 5,102,401. These applications involve slow release of antibiotic silver from the zeolite particles which is suitable for the antimicrobial fabric.

Antibiotic zeolites are well-known and can be prepared for use in the present invention using known methods. These include the antibiotic zeolites disclosed, for example, in U.S. Patent Nos. 4,938,958 and 4,911,898.

In a preferred embodiment of the invention, the inorganic antibiotic metal containing composition is an antibiotic metal salt. Such salts include silver iodate, silver iodide, silver nitrate, and silver oxide. Silver nitrate is preferred. These salts are particularly quick acting, as no release from ceramic particles is necessary to function antimicrobially.

Antibiotic ceramic particles useful with the present invention include

zeolites, hydroxyapatite, zirconium phosphates or other ion-exchange ceramics. Hydroxyapatite particles containing antimicrobial metals are described, e.g., in U.S. Patent No. 5,009,898. Zirconium phosphates containing antimicrobial metals are described, e.g., in U.S. Patent Nos. 5,296,238; 5,441,717; and 5,405,644.

5           Either natural zeolites or synthetic zeolites can be used to make the antibiotic zeolites used in the present invention. "Zeolite" is an aluminosilicate having a three dimensional skeletal structure that is represented by the formula:  $XM_2/nO \cdot Al_2O_3 \cdot YSiO_2 \cdot ZH_2O$ . M represents an ion-exchangeable ion, generally a monovalent or divalent metal ion, n represents the atomic valency of the (metal)  
10       ion, X and Y represent coefficients of metal oxide and silica respectively, and Z represents the number of water of crystallization. Examples of such zeolites include A-type zeolites, X-type zeolites, Y-type zeolites, T-type zeolites, high-silica zeolites, sodalite, mordenite, analcite, clinoptilolite, chabazite and erionite. The present invention is not restricted to use of these specific zeolites.

15           The ion-exchange capacities of these zeolites are as follows: A-type zeolite = 7 meq/g; X-type zeolite = 6.4 meq/g; Y-type zeolite = 5 meq/g; T-type zeolite = 3.4 meq/g; sodalite = 11.5 meq/g; mordenite = 2.6 meq/g; analcite = 5 meq/g; clinoptilolite = 2.6 meq/g; chabazite = 5 meq/g; and erionite = 3.8 meq/g. These ion-exchange capacities are sufficient for the zeolites to undergo  
20       ion-exchange with ammonium and antibiotic metal ions.

          The specific surface area of preferred zeolite particles is preferably at least 150 m<sup>2</sup>/g (anhydrous zeolite as standard) and the SiO<sub>2</sub>/Al<sub>2</sub>O<sub>3</sub> mol ratio in the zeolite composition is preferably less than 14, more preferably less than 11.

25           The antibiotic metal ions used in the antibiotic zeolites should be retained on the zeolite particles through an ion-exchange reaction. Antibiotic metal ions which are adsorbed or attached without an ion-exchange reaction exhibit a decreased bactericidal effect and their antibiotic effect is not long-lasting. Nevertheless, it is advantageous for imparting quick antimicrobial action to maintain a sufficient amount of surface adsorbed metal ion.

30           In the ion-exchange process, the antibiotic metal ions tend to be converted into their oxides, hydroxides, basic salts etc. either in the micro pores or on the surfaces of the zeolite and also tend to deposit there, particularly when the



concentration of metal ions in the vicinity of the zeolite surface is high. Such deposition tends to adversely affect the bactericidal properties of ion-exchanged zeolite.

5 In an embodiment of the antibiotic zeolites, a relatively low degree of ion exchange is employed to obtain superior bactericidal properties. It is believed to be required that at least a portion of the zeolite particles retain metal ions having bactericidal properties at ion-exchangeable sites of the zeolite in an amount less than the ion-exchange saturation capacity of the zeolite. In one embodiment, the zeolite employed in the present invention retains antimicrobial metal ions in an  
10 amount up to 41% of the theoretical ion-exchange capacity of the zeolite. Such ion-exchanged zeolite with a relatively low degree of ion-exchange may be prepared by performing ion-exchange using a metal ion solution having a low concentration as compared with solutions conventionally used for ion exchange.

The antibiotic metal ion is preferably present in the range of from  
15 about 0.1 to 20wt.% of the zeolite. In one embodiment, the zeolite contain from 0.1 to 20wt.% of silver ions and from 0.1 to 20wt.% of copper or zinc ions. Although ammonium ion can be contained in the zeolite at a concentration of about 20 wt.% or less of the zeolite, it is desirable to limit the content of ammonium ions to from 0.5 to 15 wt.%, preferably 1.5 to 5 wt.%. Weight% described herein is  
20 determined for materials dried at temperatures such as 110°C, 250°C or 550°C as this is the temperature employed for the preferred post-manufacturing drying process.

A preferred antibiotic zeolite is type A zeolite containing either a combination of ion-exchanged silver, zinc, and ammonium or silver and ammonium.  
25 One such zeolite is manufactured by Shinegawa, Inc. under the product number AW-10N and consists of 0.6% by weight of silver ion-exchanged in Type A zeolite particles having a diameter of about 2.5 $\mu$ . Another formulation, AJ-10N, consists of about 2% by weight silver ion-exchanged in Type A zeolite particles having a diameter of about 2.5 $\mu$ . Another formulation, AW-80, contains 0.6% by weight of  
30 silver ion-exchanged in Type A zeolite particles having a diameter of about 1.0 $\mu$ . Another formulation, AJ-80N, consists of about 2% by weight silver ion-exchanged in Type A zeolite particles having a diameter of about 1.0 $\mu$ . These zeolites

preferably contain about between 0.5% and 2.5% by weight of ion-exchanged ammonium.

In a preferred embodiment, the agent can be of the type designated HealthShield, which is sold by the assignee of the subject application. This material  
5 is basically a zeolite, this being a metal having one or the whole of the metal substituted by at least one kind of an ion exchangeable metal selected from the group consisting of Ag, Cu and Zn.

In accordance with the invention, other inorganic antimicrobial agents, i.e., those containing silver, copper, lead, gold tin, zinc and mercury. can be used.

A typical particle size for the antimicrobial agent is between 0.8 and  
10 10 microns and the agent is dispersed on the coating material 18 in the quantity of between 0.5 and 25% by weight, more preferably between 0.5 and 10% and most preferably between 1.5 and 5% of the matter that remains on the fabric, exclusive of the fabric. The particles adhere to the coating material while it is wet and  
15 become embedded in the coating material 18 as it dries.

As shown in Fig. 4, after the antimicrobial agent 20 is applied to the coating material 18, the product is cured, that is, dried, with air under pressure, for example at 60 psi. This removes all of the matter, coating material and antimicrobial agent, in the fabric pores 14. As shown, each of the fabric fibers  
20 has on one surface thereof the coating material 18 on top of which are the embedded particles of the antimicrobial agent 20. If both surfaces of the fabric are treated, the entirety of the fabric would have the same appearance. In any case, the fabric pores 14 would be clear. This maintains fabric pliability.

In another embodiment of making the antimicrobial fabric, the  
25 inorganic antimicrobial agent is blended into the textile coating material mixture, such as of the type described above. The mixture is then applied to the base fabric by a spraying process, as previously described, or by dipping. Here also, the fabric is preferably held under tension. In each type of application of the mixture, the wet material is subjected to a blowing operation to remove matter from the pores so  
30 that it will retain its porosity. The coating materials can include, for example, acrylic, polyurethane, silicone, latex, polyglycolic lactic acid or other biodegradable polymer, especially one that is a hydrophilic, a non-degrading polymer such as a

hydrophilic polyurethane, for example TECOPHILIC which is made by Thermedics. Use of antimicrobial agents in hydrophilic materials is also described in an application filed on even date herewith, assigned attorney docket number 1985/OE556 and entitled "Antibiotic Hydrophilic Polymer Coating". The inorganic antimicrobial agent mixed with the coating material is one of the type discussed above and the concentration of the agent in the dry coating material is 0.01 to 50%, preferably 0.1 to 20% and most preferably from 0.5 to 10%.

The resulting fabric, made either by applying the inorganic agent to an adherent coating material or as part of a mixture with the coating material, is a piece of fabric that is antimicrobial, pliable and porous. The product can be used in medical applications and has antimicrobial properties.

An example of an embodiment of the porous fabric of the invention utilized the following:

fiber material:	polyester
silicone mixture:	50% RTV and 50% xylene
thickness of silicone layer:	1-5 microns
agent particle size:	1-2.5 microns
agent dispersal factor:	1%
air pressure:	60 psi

Non-Porous Fabric - Using the process of Figs. 1-4 and the described components and their variants, by eliminating the drying step by air under pressure and permitting drying of the fabric in a manner which does not remove the matter from the pores, the fabric will be fully coated with the inorganic agent. That is, the antimicrobial agent will be embedded in the coating material of the fabric fibers as well as in the fabric pores. Here, it is not absolutely necessary to hold the fabric under tension when the agent is applied to the fabric and the drying takes place. While the resulting fabric will not be as flexible, it still is satisfactory for use as a suturing ring.

Another way of making the non-porous antimicrobial fabric, other than by spraying the inorganic onto the fabric or dipping the fabric into the inorganic, is to provide a slurry of the inorganic and kneading it into the base fabric. A process

of this type is described in U.S. patent 5,100,671. Here also the antimicrobial agent will remain in the fabric pores.

Fabric With Integral Antimicrobial Agent In this type of fabric, the fibers are either of a plurality of the mono-filament type, such as of a plurality of polyester filaments, formed in bundles, such as by twisting, or of a naturally multi-filament type, such as cotton. The object is that the fibers themselves have spaces, gaps or voids into which the antimicrobial agent can be placed. For example, a dough or slurry of the antimicrobial agent is kneaded into a fabric of this type and the agent will be embedded in the spaces of the bundle of the plurality of mono-filaments forming a fiber or the fiber of natural material. The fabric can be made porous by holding it under tension and blowing out the agent from the pores, as described above. It can be left non-porous by permitting the agent to dry without attempting to remove the particles from the pores.

Antimicrobial Fabric Coated With Tissue Compatible Material - The porous fabric described above with respect to Figs. 1-4, or the non-porous fabric, can be coated with a tissue-growth promoting substance, for example, collagen. The collagen can be coated onto the fabric either before or after the fabric is shaped into the suturing ring. The collagen can be coated on one or both sides of the fabric and can be applied by spraying, dipping, painting, layering or any other suitable process. It is applied at least to the surface that is to be remote from the valve body, that is, exposed to the body tissue. The collagen material still permits the inorganic antimicrobial agent of the fabric to perform its function since it is effectively porous, being a skin type material.

Figure 5 is a perspective view of a preferred embodiment of suturing ring 70 using the fabric containing an inorganic antimicrobial agent of the porous or non-porous types, whether coated with collagen or un-coated, as described above. The ring 70 has a top portion shoulder 72 of generally annular shape and a central opening 73. A step wall 74 depends downwardly from the annular shoulder 72 and at the bottom end of the step wall is an outwardly extending is an circumferential flange 76. The valve body, illustratively shown by 80 and illustratively shown as being of disc shape, fits within the ring between the shoulder 72 and the flange 76. The height of the step wall 74 generally

corresponds to the height of the valve body 80. The opening 73 at the top of the ring can be reinforced, such as by stitching 77, so that the valve body can be firmly engaged.

To attach the heart valve body 80 to the heart, the body is placed within the ring 70 and oriented with the ring flange 76 positioned opposite the heart tissue. The surgeon then makes sutures through the flange 76 to the heart tissue. The valve body 80 will be firmly held relative to the heart between the flange 76 and the shoulder 72 with its reinforcement 77.

Once the valve body is attached, the inorganic antimicrobial agent of the suturing ring 70 fabric functions to kill bacteria from body parts and fluid that contact it. Thus, the suturing ring provides an added degree of protection against infection.

When the ring 70 is made of the porous fabric there is an advantage in that the porosity of the fabric allows fluid access to the valve body which maintains better temperature stability between the valve body and the heart.

Whether the fabric is porous or non-porous, it is preferred that the fabric forming the ring have the antimicrobial agent on both surfaces so that it also will be more active against bacteria and organisms between the ring and the heart valve body.

The ring 70 can be formed from the fabric by any suitable technique, such as cutting a piece of the fabric to size, making the opening 73, etc. Since the fabric 70 has the coating material 18, which can have shape retaining characteristics, some types of the fabric can be shaped by pressure or heat, or combination of the two, depending on the type of coating material. For example, if the fabric coating material 18 to which the agent is applied is an acrylic or other material with thermosetting properties, a slightly heated die can be used having the shape of ring 70. The heating is carried out at a level such as not to remove the coating material. If the fabric is to be heated to shape it into the ring, it is preferred that the collagen be applied after the heating.

The suturing ring 70 shown in Fig. 5 is only illustrative of the various types of rings that can be produced using the fabric of the invention which, as explained above, has the necessary antimicrobial properties as well as being able to

be easily formed in the shape shown as well as to permit its attachment to tissue by sutures. In all cases, the antimicrobial action of the fabric reduces the possibility of infection occurring at the valve implantation site.

5 In some cases a suturing ring is used with a heart valve body that is non-circular or in which it is desired to be able to position the suturing ring relative to the body. Various arrangements for doing this are shown in U.S. patent 5,766,240. One of the embodiments of that patent is shown in Figs. 6 and 6A adapted for using the novel inorganic antimicrobial fabric of the invention.

10 Referring to Figs. 6 and 6A, there is an annular collar 90 having upper and lower sections 91 and 93 between which is a depressed center section 92 which extends inwardly of sections 91 and 93. The collar center section 92 is to fit into a corresponding peripheral depression 82 in the outer wall of the valve body 80. Here the suturing ring 170 is formed by taking a piece of the fabric 170, laying it between the valve body groove 82 and the collar center section 92 which is  
15 press fit in the valve body groove 82. The fabric is played out to form a loose loop 174 of the fabric and the fabric ends are sewn at 176 to complete the ring. There are wraps of a cord 177 around the collar center section to prevent it from being damaged by a needle inadvertently making contact.

20 In using the arrangement of Figs. 6 and 6A, the collar 90 holds the fabric suturing ring 170 in position relative to the valve body and is rotatable about the valve body to position the ring 170, as desired. The surgeon can manipulate the loose hanging ring loop 174, such as by pulling part of it down, so that sutures can be made through the ring 170 to the heart tissue. The use of the antimicrobial fabric is particularly advantageous in this type of a suturing ring since body fluid  
25 can be present in the space between the collar and the inner part of the ring which could create infection problems. The antimicrobial action of the fabric acts to prevent this.

30 The antibiotic properties of the antibiotic zeolite particles of the invention may be assayed while in aqueous formulations using conventional assay techniques, including for example determining the minimum growth inhibitory concentration (MIC) with respect to a variety of bacteria, eumycetes and yeast. In such a test, the bacteria listed below may be employed:

Bacillus cereus var mycoides,  
Escherichia coli,  
Pseudomonas aeruginosa,  
Staphylococcus aureus,  
5 Streptococcus faecalis,  
Aspergillus niger,  
Aureobasidium pullulans,  
Chaetomium globosum,  
Gliocladium virens,  
10 Penicillium funiculosum,  
Candida albicans,  
Saccharomyces cerevisiae,

The assay for determining MIC can be carried out by smearing a solution containing bacteria for inoculation onto a plate culture medium to which a  
15 test sample of the encapsulated antibiotic zeolite particles is added in a particular concentration, followed by incubation and culturing of the plate. The MIC is defined as a minimum concentration thereof required for inhibiting the growth of each bacteria.

20 The present invention will hereunder be explained in more detail with reference to the following non-limiting working examples.

#### Example 1

A 1" x 1" sample of knitted polyester, available from Bard Vascular Systems Division as knitted polyester style no. 6103, was coated with an antibiotic  
25 hydrophilic coating as follows.

A coating solution containing 2.90% by weight of hydrophilic polyurethane available as Tecophilic™ from Thermedics; 96.81% tetrahydrofuran; and 0.29% AW-10N zeolite, available from Shinagawa, Inc., was prepared and mixed with a high shear mixer.

30 An eye dropper was used to apply the coating solution to the polyester sample. The polyester sample was then sprayed with air to remove excess powder and cure the coating.

Example 2

A Dow Shaker Test was performed on the polyester sample prepared in Example 1 (hereafter referred to as Sample A) to determine its inhibitory effect against *S. aureus*. The Dow Shaker Test is based on Dow Corporate Test Method 0923 for testing aerobic bacteria by Dow Chemical. The Dow Shaker Test is described below.

Sample A was sterilized at 121 °C for 15 minutes.

A culture tube containing *S. aureus* was prepared by adding one disk of *S. aureus* to the culture tube. From about 2 to 5 ml of broth was added to the culture tube. Then the culture tube was agitated with a vortex mixer until the disk was completely dissolved in the broth. The bacteria in the culture tube was incubated for at least 3 hours at 35 °C. The culture tube was then refrigerated at about 2-8 °C until needed for testing.

A 5 ml sample of bacteria from the culture tube was removed and agitated in a vortex mixer. The absorbance of the sample was measured at 475 nm with a spectrophotometer relative to the absorbance of the aforementioned broth. Broth and/or bacteria from the culture tube were added to the sample until an absorbance of about 0.1 absorbance units was obtained. This corresponded to from about  $10^5$  to about  $10^6$  colony forming units per milliliter (CFU/ml).

5 ml of suspension was extracted from the sample and added to a flask containing 70 ml of sterile buffer. The resulting solution contained from about  $10^4$  to about  $10^5$  CFU/ml. The flask was capped and shaken on a wrist action shaker for 1 minute at maximum speed. This is referred to as time "0 hours" below.

The number of colony forming units in 1 ml of the solution was determined at time 0 hours by the following procedure. 1 ml of solution was extracted from the flask and added to a vial containing 9 ml of buffer solution to form a 10:1 dilution. The solution was repeatedly diluted with buffer solution until a plate count of about 30 to about 200 CFU/ml was obtained.

1 ml of the solution from the flask and each dilution were transferred to separate petri dishes. About 15-20 ml of molten agar was added to each dish. Each dish was rotated 10 times clockwise and 10 times counter-clockwise to



evenly distribute the agar and bacteria. Then, each dish was incubated for 18-24 hours at 35 °C. A plate count was performed on the petri dish containing from about 30 to about 200 bacteria colony forming units to determine the number of colony forming units.

Also, at time 0 hours, sample A was added to the flask and shaken with a wrist action shaker for 1 hour. The number of colony forming units in 1 ml of the solution in the flask was determined by the procedure above using 2 petri dishes. If the numbers of colony forming units in the 2 petri dishes were not within 15% of each other, the entire Dow Shaker Test was repeated.

The number of colony forming units in 1 ml of the solution was also determined after shaking the flask with a wrist action shaker for 18 and 24 hours.

A control was tested by the same procedure as sample A. The control was a 1" x 1" sample of knitted polyester, available from Bard Vascular Systems Division as knitted polyester style no. 6103.

The number of colony forming units at times 0 hours, 1 hour, 18 hours, and 24 hours for sample A and the control are in Table 1. The percentage of bacteria killed by sample A and the control at times 1 hour, 18 hours, and 24 hours are in Table 2.

Table 1

Sample	Bacteria Counts of <i>S. aureus</i> (Colony Forming Units)			
	0 hours	1 hour	18 hours	24 hours
Sample A	780,000	2,145,000	85,000	3,700
Control	480,000	12,400,00	4,720,00	4,300,000

Table 2

Sample	% Killed		
	1 hour	18 hours	24 hours
Sample A	0	89.10%	99.53%
Control	0	0	0

As indicated in Table 2, Sample A exhibited 99.53% inhibition of *S. aureus* after 24 hours of contact with the bacteria.

### Example 3

Safety and biocompatibility tests were conducted on the antibiotic zeolites employed in the invention. ISO 10993-1 procedures were employed. The following results were obtained: ,

Cytotoxicity: <b>Non-Toxic</b>
Acute Systemic Toxicity: <b>Non-Toxic</b>
Intracutaneous Toxicity: <b>Passed</b>
Skin Irritation Test: <b>Non-Irritant</b>
Chronic Toxicity: <b>No Observable Effect</b>
<i>In-vitro</i> Hemolysis: <b>Non-Hemolytic</b>
30-day Muscle Implant Test: <b>Passed</b>
60-day Muscle Implant Test: <b>Passed</b>
90-day Muscle Implant Test: <b>Passed</b>
Ames Mutagenicity Test: <b>Passed</b>
Pyrogenicity: <b>Non-Pyrogenic</b>

Thus, the antibiotic zeolites are exceptionally suitable under relevant toxicity and biocompatibility standards for use in the fabric.

**WE CLAIM:**

1                   1. An implantable heart valve having at least one heart valve  
2 mechanism, and a suturing ring of a fabric containing an inorganic antimicrobial  
3 agent to attach said valve body to heart tissue by passing sutures through said  
4 ring.

1                   2. An implantable heart valve as in claim 1 wherein said fabric is  
2 porous.

1                   3. An implantable heart valve as in claim 1 wherein said fabric is  
2 coated with collagen.

1                   4. An implantable heart valve as in claim 1 wherein said valve has a  
2 body with top and bottom surfaces and a wall there between, said suturing ring  
3 having an annular top part fitting over one of said top and bottom surfaces and  
4 defining an opening to said heart valve and a step wall depending from said  
5 annular top part to extend along said valve body wall.

1                   5. An implantable heart valve as in claim 4 wherein said suturing ring  
2 further comprises a flange ring extending outwardly from the end of said step wall  
3 opposite said annular top part.

1                   6. An implantable heart valve as in claim 1 wherein the fibers of said  
2 fabric are coated with a coating material having embedded particles of an inorganic  
3 antimicrobial agent, and said coating material is elastomeric.

1                   7. An implantable heart valve as in claim 6 wherein said coating  
2 material is selected from the group consisting of acrylic, polyurethane, silicone,  
3 latex, polyglycolic lactic acid, a biodegradable polymer, a hydrophilic biodegradable  
4 polymer, and a non-degrading polymer.

1                   8. An implantable heart valve as in claim 7 wherein said non-  
2 degrading polymer is a hydrophilic polyurethane.

1                   9. An implantable heart valve as in claim 1 wherein the fibers of said  
2 fabric are selected from the group consisting of cotton, nylon, polyester, Teflon, e-  
3 PTFE and blends of these materials.

1                   10. An implantable heart valve as in claim 1 wherein said  
2 antimicrobial agent is a metal.

1                   11. An implantable heart valve as in claim 1 wherein said  
2 antimicrobial agent is a zeolite.

1                   12. An implantable heart valve as in claim 6 wherein said  
2 agent is dispersed on the coating material in the quantity of between 0.5 and 20%,  
3 more preferably between 0.5 and 10% and most preferably between 1.5 and 5.0%  
4 of the matter that remains on the fabric, exclusive of the fabric.

1                   13. An implantable heart valve as in claim 12 wherein the particle  
2 size of said agent is between 0.8 and 10 microns.

1                   14. An implantable heart valve as in claim 6 wherein the fiber of said  
2 fabric is polyester, said coating material is a hydrophilic polymer and said agent is a  
3 zeolite.

1                   15. A suturing ring to attach the body of an implantable heart valve  
2 to body tissue comprising a ring of fabric having a portion to contact the valve  
3 body and a portion for accepting sutures to be fastened to the body tissue, said  
4 fabric containing an inorganic antimicrobial agent.

1                   16. A suturing ring as in claim 15 wherein said fabric is coated with  
2 collagen.

1 17. A suturing ring as in as in claim 15 wherein said fabric is porous.

1 18. A suturing ring as in claim 17 wherein said fabric is coated with  
2 collagen.





1 19. A suturing ring as in claim 15 wherein the fibers of said fabric  
2 piece are of a type having voids and said antimicrobial agent in said voids.


1 20. A suturing ring as in claim 15 wherein said fabric is non-porous  
2 and said antibiotic agent is over the entirety of said fabric.

1 21. A suturing ring as in claim 20 further comprising a coating of a  
2 tissue compatible material on said fabric.

1 22. A suturing ring as in claim 15 wherein the valve body has top  
2 and bottom surfaces and a wall there between, said suturing ring portion for  
3 contacting the body having an annular top part to fit over one of said top and  
4 bottom surfaces and defining an opening to said heart valve and a step wall  
5 depending from said annular top part to extend along said valve body wall.

1 23. A suturing ring as in claim 15 further comprises a flange ring  
2 extending outwardly from the end of said step wall opposite said annular top part.








FIG. 6




FIG. 6A





## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b>  <b>A61F 2/24</b>	<b>A2</b>	<b>(11) International Publication Number:</b> <b>WO 00/30567</b>  <b>(43) International Publication Date:</b> 2 June 2000 (02.06.00)
<b>(21) International Application Number:</b> PCT/US99/27272  <b>(22) International Filing Date:</b> 16 November 1999 (16.11.99)  <b>(30) Priority Data:</b> 09/197,808      23 November 1998 (23.11.98)      US  <b>(71) Applicant:</b> HEALTHSHIELD TECHNOLOGIES LLC [US/US]; Suite 201, 67 Prospect Avenue, West Hartford, CT 06106 (US).  <b>(72) Inventors:</b> HOLLEY, Steven; 24 Bigelow Street, Brighton, MA 02135 (US). BARRY, John, E.; 18 Drake Lane, Derry, NH 03038 (US). TROGOLO, Jeffrey, A.; 228 Commonwealth Avenue, Boston, MA 02116 (US).  <b>(74) Agents:</b> GOGORIS, Adda, C. et al.; Darby & Darby P.C., 805 Third Avenue, New York, NY 10022-7513 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>Without international search report and to be republished          upon receipt of that report.</i>
<b>(54) Title:</b> ANTIMICROBIAL SUTURING RING FOR HEART VALVE  <b>(57) Abstract</b>  <p>A suturing ring to attach the body of an implantable heart valve to heart tissue by sutures is composed of a fabric containing an inorganic antimicrobial agent. The fabric can have a material coating the fibers of the fabric in which particles of the agent are embedded. The coating material can be elastomeric and the fabric porous, to improve its flexibility, or non-porous and the fabric ring can be coated with a tissue compatible substance such as collagen. One type of ring has an annular top part to fit over one of top and bottom surfaces of the valve body and defining an opening to the heart valve, a step wall depending from the annular top part to extend along said valve body wall and an outwardly extending flange through which the sutures are to be sewn.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## ANTIMICROBIAL SUTURING RING FOR HEART VALVE

Modern implantable prosthetic heart valves are typically formed of an annular valve seat in a relatively rigid valve body. One or more valve members, such as spheres, disks or leaflets, are movable between a closed, seated position in the annular valve seat and an open position over a prescribed range of motion. Such mechanical heart valves are typically formed of blood compatible, non-thrombogenic materials, typically currently comprising pyrolytic carbon and titanium. The rigid valve body is formed of a biocompatible material, such as a suitable metal or plastic. Valves made of human and porcine tissue also have been developed.

Some types of heart valves utilize a suturing ring surrounding the valve body. The ring is to be sewn by the surgeon to the peripheral tissue of a natural heart valve orifice (the "the valve rim") after surgical removal of damaged or diseased natural valve structure. The suturing ring is made of a fabric or other similar material which can be penetrated by the needle used by the surgeon to fasten the valve body to the heart tissue. In some cases, the suturing ring includes a part to which the fabric is fastened so that the ring can be rotated relative to the heart valve body. Such an arrangement is shown in U.S. patent 5,766,240.

### Brief Description of the Invention

The present invention relates to a suturing ring for a heart valve body containing an inorganic antimicrobial agent. In a preferred embodiment the ring is of fabric material. The antimicrobial properties of such a suturing ring has advantages in that it is able to kill certain types of bacteria which are present in the body and which, at least in the initial stages of implantation of the heart valve, can have adverse effects relative to infection and rejection of the valve and also its

proper operation. The antimicrobial fabric of the suturing ring of the invention is biocompatible, and presents no problem relative to its suturing by the surgeon. In a preferred embodiment of the invention, the antimicrobial agent is a zeolite.

5 The antimicrobial fabric for the suturing ring can be of a porous flexible material to accommodate heart movement or of a fabric that is fully coated with the antimicrobial agent. In either case, the fabric can be coated with a tissue compatible substance such as collagen.

10 The invention also provides a novel suturing ring having fabric material with an inorganic antimicrobial with the ring being rotatable relative to the heart valve body to permit its positioning relative to the heart tissue orifice.

#### Objects of the Invention

It is therefore an object of the invention to provide a heart valve suturing ring including a fabric containing an inorganic antimicrobial agent

15 Another object is to provide a suturing ring for a heart valve of porous fabric containing an inorganic antimicrobial agent.

An additional object is to provide a fabric suturing ring for a heart valve containing an inorganic antimicrobial agent which is coated by a tissue compatible substance.

20 Still a further object is provide a suturing ring for a heart valve having a fabric containing an inorganic antimicrobial agent which is rotatable relative to the heart valve body.

#### Brief Description of the Drawings

25 Other objects and advantages of the present invention will become more apparent upon reference to the following specification and annexed drawings in which:

Fig. 1 is a perspective view of a base fabric;

Fig. 2 is a cross-sectional view along lines 2-2 of Fig.1

30 showing application of the coating material to the fabric;

Fig. 3 is a cross-sectional view of the fabric after the antimicrobial agent has been applied;

Fig. 4 is a cross-sectional view of the finished fabric after drying;

Fig. 5 is a perspective view of a heart valve fabric suturing ring according to the invention and Fig. 5A is a cross-section thereof;

Fig. 6 is perspective view of a rotatable collar for a suturing ring and

Fig. 6A is a cross sectional view showing the fabric of the invention applied.

#### Detailed Description of the Invention

All patents, patent applications, and publications listed herein are hereby incorporated by reference in their entireties.

Various types of fabrics containing the antimicrobial agent suitable for use as the suturing ring are first described.

1. Porous Fabric - Figs. 1-4 show an embodiment of the invention for processing a fabric that is porous and flexible to be used for the suturing ring. Referring to Fig. 1, there is shown a base material comprising a piece of fabric 10 of the mesh type formed by fibers 12 which are laid transverse to each other and which define spaces, or pores, 14 between the fibers. The fibers can be of any suitable material, for example, cotton, nylon polyester, Teflon, e-PTFE and blends of these materials. For the suturing ring application, Teflon or polyester is preferred. The fabric can be either of the woven or non-woven type. The fabric 10 is shown by the arrows T as being able to be held under tension in both directions generally along the fabric length and width by any suitable mechanism (not shown), for example, rollers, clamps, etc.

Fig. 2 shows the fabric piece 10 in the stage of having a coating of an adherent material 18 applied to one surface. It should be understood that the invention is applicable to performing the process on both fabric surfaces and on the sides which form the pores 14. The adherent coating material 18 is a biologically compatible material such as, for example, acrylic, polyurethane, silicone, latex, polyglycolic lactic acid or other biodegradable polymer, especially one that is a hydrophilic, non-degrading polymer such as a hydrophilic polyurethane, for example TECOPHILIC which is made by Thermedics. These materials all have elastomeric properties.

In a preferred embodiment of the invention, the fabric coating material

18 is applied as a mixture of a high strength RTV dispersed in a solvent, such as xylene. A preferred composition of the mixture is 50% RTV and 50% xylene although the ratio of the two materials can be varied. Increasing the proportion of the coating material in the mixture makes the final product less pliable.

5 In a preferred manner of application of the coating material 18, the fabric 10 is held under tension in its lengthwise dimension. The coating material-solvent mixture is supplied by a peristaltic pump to an ultrasonic disperser. The ultrasonic disperser creates a fine mist of the mixture that is blown out of the disperser by an air source, illustratively shown by reference numeral 19, to coat the fabric 10. There can be one or more dispersers and air sources on both sides of the fabric and at varying angles to fully coat the entire surfaces of the fabric fibers. Alternatively, only one surface is coated, the two surfaces are coated sequentially, or both surfaces coated at the same time. In the application for the suturing ring the fabric is coated on both surfaces.

15 Fig. 3 shows the fabric 10 having been coated on one side with the coating material mixture. As seen, the coating material 18 extends into the openings 14 between the fibers of the fabric and also coats the top of each of the fibers. There is a continuous layer of the coating material 18 over the fabric at this stage of the process, that is, the coating material fills the pores 14. The fabric can be cycled relative to the disperser as many times as needed. That is, the deposition of the coating material mixture on the fabric can be accomplished by applying a desired number of layers to achieve a desired thickness. The layers are contiguous to and mixed with each other. The depth of the coating material 18 on top of the fabric is selected to be between 0.01 and 50 microns, more preferably between 0.1 and 25 microns, and most preferably between 0.1 and 10 microns.

20 As is also shown in Fig. 3, an inorganic antimicrobial agent 20 in powdered form is applied to the coating material 18 while it is still wet. During this step the fabric preferably is held under tension in both directions, that is, generally along both the fabric fibers' cross-direction. The powdered antimicrobial agent 20 becomes immersed into and bonds with the coating material layer 18 on the fabric. The xylene evaporates from the coating.

30 As to the inorganic antimicrobial agent 20, a number of metal ions,

which are inorganic materials, have been shown to possess antibiotic activity, including silver, copper, zinc, mercury, tin, lead, bismuth, cadmium, chromium and thallium ions. These antibiotic metal ions are believed to exert their effects by disrupting respiration and electron transport systems upon absorption into bacterial or fungal cells. Antimicrobial metal ions of silver, gold, copper and zinc, in particular, are considered safe even for *in vivo* use. Antimicrobial silver ions are particularly useful for *in vivo* use due to the fact that they are not substantially absorbed into the body. That is, if such materials are used for the antimicrobial fabric, they should pose no hazard to the body.

Antibiotic zeolites also are suitable as the agent. These have been prepared by replacing all or part of the ion-exchangeable ions in zeolite with ammonium ions and antibiotic metal ions, as described in U.S. Patent Nos. 4,938,958 and 4,911,898. Such zeolites have been incorporated in antibiotic resins (as shown in U.S. Patent Nos. 4,938,955 and 4,906,464) and polymer articles (U.S. Patent No. 4,775,585). Polymers including the antibiotic zeolites have been used to make refrigerators, dish washers, rice cookers, plastic film, chopping boards, vacuum bottles, plastic pails, and garbage containers. Other materials in which antibiotic zeolites have been incorporated include flooring, wall paper, cloth, paint, napkins, plastic automobile parts, catheters, bicycles, pens, toys, sand, and concrete. Examples of such uses are described in U.S. Patents 5,714,445; 5,697,203; 5,562,872; 5,180,585; 5,714,430; and 5,102,401. These applications involve slow release of antibiotic silver from the zeolite particles which is suitable for the antimicrobial fabric.

Antibiotic zeolites are well-known and can be prepared for use in the present invention using known methods. These include the antibiotic zeolites disclosed, for example, in U.S. Patent Nos. 4,938,958 and 4,911,898.

In a preferred embodiment of the invention, the inorganic antibiotic metal containing composition is an antibiotic metal salt. Such salts include silver iodate, silver iodide, silver nitrate, and silver oxide. Silver nitrate is preferred. These salts are particularly quick acting, as no release from ceramic particles is necessary to function antimicrobially.

Antibiotic ceramic particles useful with the present invention include

zeolites, hydroxyapatite, zirconium phosphates or other ion-exchange ceramics. Hydroxyapatite particles containing antimicrobial metals are described, e.g., in U.S. Patent No. 5,009,898. Zirconium phosphates containing antimicrobial metals are described, e.g., in U.S. Patent Nos. 5,296,238; 5,441,717; and 5,405,644.

5           Either natural zeolites or synthetic zeolites can be used to make the antibiotic zeolites used in the present invention. "Zeolite" is an aluminosilicate having a three dimensional skeletal structure that is represented by the formula:  $XM_2/nO \cdot Al_2O_3 \cdot YSiO_2 \cdot ZH_2O$ . M represents an ion-exchangeable ion, generally a monovalent or divalent metal ion, n represents the atomic valency of the (metal)  
10           ion, X and Y represent coefficients of metal oxide and silica respectively, and Z represents the number of water of crystallization. Examples of such zeolites include A-type zeolites, X-type zeolites, Y-type zeolites, T-type zeolites, high-silica zeolites, sodalite, mordenite, analcite, clinoptilolite, chabazite and erionite. The present invention is not restricted to use of these specific zeolites.

15           The ion-exchange capacities of these zeolites are as follows: A-type zeolite = 7 meq/g; X-type zeolite = 6.4 meq/g; Y-type zeolite = 5 meq/g; T-type zeolite = 3.4 meq/g; sodalite = 11.5 meq/g; mordenite = 2.6 meq/g; analcite = 5 meq/g; clinoptilolite = 2.6 meq/g; chabazite = 5 meq/g; and erionite = 3.8 meq/g. These ion-exchange capacities are sufficient for the zeolites to undergo  
20           ion-exchange with ammonium and antibiotic metal ions.

          The specific surface area of preferred zeolite particles is preferably at least 150 m<sup>2</sup>/g (anhydrous zeolite as standard) and the SiO<sub>2</sub>/Al<sub>2</sub>O<sub>3</sub> mol ratio in the zeolite composition is preferably less than 14, more preferably less than 11.

25           The antibiotic metal ions used in the antibiotic zeolites should be retained on the zeolite particles through an ion-exchange reaction. Antibiotic metal ions which are adsorbed or attached without an ion-exchange reaction exhibit a decreased bactericidal effect and their antibiotic effect is not long-lasting. Nevertheless, it is advantageous for imparting quick antimicrobial action to maintain a sufficient amount of surface adsorbed metal ion.

30           In the ion-exchange process, the antibiotic metal ions tend to be converted into their oxides, hydroxides, basic salts etc. either in the micro pores or on the surfaces of the zeolite and also tend to deposit there, particularly when the



concentration of metal ions in the vicinity of the zeolite surface is high. Such deposition tends to adversely affect the bactericidal properties of ion-exchanged zeolite.

In an embodiment of the antibiotic zeolites, a relatively low degree of ion exchange is employed to obtain superior bactericidal properties. It is believed to be required that at least a portion of the zeolite particles retain metal ions having bactericidal properties at ion-exchangeable sites of the zeolite in an amount less than the ion-exchange saturation capacity of the zeolite. In one embodiment, the zeolite employed in the present invention retains antimicrobial metal ions in an amount up to 41% of the theoretical ion-exchange capacity of the zeolite. Such ion-exchanged zeolite with a relatively low degree of ion-exchange may be prepared by performing ion-exchange using a metal ion solution having a low concentration as compared with solutions conventionally used for ion exchange.

The antibiotic metal ion is preferably present in the range of from about 0.1 to 20wt.% of the zeolite. In one embodiment, the zeolite contain from 0.1 to 20wt.% of silver ions and from 0.1 to 20wt.% of copper or zinc ions. Although ammonium ion can be contained in the zeolite at a concentration of about 20 wt.% or less of the zeolite, it is desirable to limit the content of ammonium ions to from 0.5 to 15 wt.%, preferably 1.5 to 5 wt.%. Weight% described herein is determined for materials dried at temperatures such as 110°C, 250°C or 550°C as this is the temperature employed for the preferred post-manufacturing drying process.

A preferred antibiotic zeolite is type A zeolite containing either a combination of ion-exchanged silver, zinc, and ammonium or silver and ammonium. One such zeolite is manufactured by Shinegawa, Inc. under the product number AW-10N and consists of 0.6% by weight of silver ion-exchanged in Type A zeolite particles having a diameter of about 2.5 $\mu$ . Another formulation, AJ-10N, consists of about 2% by weight silver ion-exchanged in Type A zeolite particles having a diameter of about 2.5 $\mu$ . Another formulation, AW-80, contains 0.6% by weight of silver ion-exchanged in Type A zeolite particles having a diameter of about 1.0 $\mu$ . Another formulation, AJ-80N, consists of about 2% by weight silver ion-exchanged in Type A zeolite particles having a diameter of about 1.0 $\mu$ . These zeolites

preferably contain about between 0.5% and 2.5% by weight of ion-exchanged ammonium.

In a preferred embodiment, the agent can be of the type designated HealthShield, which is sold by the assignee of the subject application. This material is basically a zeolite, this being a metal having one or the whole of the metal substituted by at least one kind of an ion exchangeable metal selected from the group consisting of Ag, Cu and Zn.

In accordance with the invention, other inorganic antimicrobial agents, i.e., those containing silver, copper, lead, gold tin, zinc and mercury. can be used.

A typical particle size for the antimicrobial agent is between 0.8 and 10 microns and the agent is dispersed on the coating material 18 in the quantity of between 0.5 and 25% by weight, more preferably between 0.5 and 10% and most preferably between 1.5 and 5% of the matter that remains on the fabric, exclusive of the fabric. The particles adhere to the coating material while it is wet and become embedded in the coating material 18 as it dries.

As shown in Fig. 4, after the antimicrobial agent 20 is applied to the coating material 18, the product is cured, that is, dried, with air under pressure, for example at 60 psi. This removes all of the matter, coating material and antimicrobial agent, in the fabric pores 14. As shown, each of the fabric fibers has on one surface thereof the coating material 18 on top of which are the embedded particles of the antimicrobial agent 20. If both surfaces of the fabric are treated, the entirety of the fabric would have the same appearance. In any case, the fabric pores 14 would be clear. This maintains fabric pliability.

In another embodiment of making the antimicrobial fabric, the inorganic antimicrobial agent is blended into the textile coating material mixture, such as of the type described above. The mixture is then applied to the base fabric by a spraying process, as previously described, or by dipping. Here also, the fabric is preferably held under tension. In each type of application of the mixture, the wet material is subjected to a blowing operation to remove matter from the pores so that it will retain its porosity. The coating materials can include, for example, acrylic, polyurethane, silicone, latex, polyglycolic lactic acid or other biodegradable polymer, especially one that is a hydrophilic, a non-degrading polymer such as a

hydrophilic polyurethane, for example TECOPHILIC which is made by Thermedics. Use of antimicrobial agents in hydrophilic materials is also described in an application filed on even date herewith, assigned attorney docket number 1985/OE556 and entitled "Antibiotic Hydrophilic Polymer Coating". The inorganic antimicrobial agent mixed with the coating material is one of the type discussed above and the concentration of the agent in the dry coating material is 0.01 to 50%, preferably 0.1 to 20% and most preferably from 0.5 to 10%.

The resulting fabric, made either by applying the inorganic agent to an adherent coating material or as part of a mixture with the coating material, is a piece of fabric that is antimicrobial, pliable and porous. The product can be used in medical applications and has antimicrobial properties.

An example of an embodiment of the porous fabric of the invention utilized the following:

fiber material:	polyester
silicone mixture:	50% RTV and 50% xylene
thickness of silicone layer:	1-5 microns
agent particle size:	1-2.5 microns
agent dispersal factor:	1 %
air pressure:	60 psi

Non-Porous Fabric - Using the process of Figs. 1-4 and the described components and their variants, by eliminating the drying step by air under pressure and permitting drying of the fabric in a manner which does not remove the matter from the pores, the fabric will be fully coated with the inorganic agent. That is, the antimicrobial agent will be embedded in the coating material of the fabric fibers as well as in the fabric pores. Here, it is not absolutely necessary to hold the fabric under tension when the agent is applied to the fabric and the drying takes place. While the resulting fabric will not be as flexible, it still is satisfactory for use as a suturing ring.

Another way of making the non-porous antimicrobial fabric, other than by spraying the inorganic onto the fabric or dipping the fabric into the inorganic, is to provide a slurry of the inorganic and kneading it into the base fabric. A process

of this type is described in U.S. patent 5,100,671. Here also the antimicrobial agent will remain in the fabric pores.

Fabric With Integral Antimicrobial Agent In this type of fabric, the fibers are either of a plurality of the mono-filament type, such as of a plurality of polyester filaments, formed in bundles, such as by twisting, or of a naturally multi-filament type, such as cotton. The object is that the fibers themselves have spaces, gaps or voids into which the antimicrobial agent can be placed. For example, a dough or slurry of the antimicrobial agent is kneaded into a fabric of this type and the agent will be embedded in the spaces of the bundle of the plurality of mono-filaments forming a fiber or the fiber of natural material. The fabric can be made porous by holding it under tension and blowing out the agent from the pores, as described above. It can be left non-porous by permitting the agent to dry without attempting to remove the particles from the pores.

Antimicrobial Fabric Coated With Tissue Compatible Material - The porous fabric described above with respect to Figs. 1-4, or the non-porous fabric, can be coated with a tissue growth promoting substance, for example, collagen. The collagen can be coated onto the fabric either before or after the fabric is shaped into the suturing ring. The collagen can be coated on one or both sides of the fabric and can be applied by spraying, dipping, painting, layering or any other suitable process. It is applied at least to the surface that is to be remote from the valve body, that is, exposed to the body tissue. The collagen material still permits the inorganic antimicrobial agent of the fabric to perform its function since it is effectively porous, being a skin type material.

Figure 5 is a perspective view of a preferred embodiment of suturing ring 70 using the fabric containing an inorganic antimicrobial agent of the porous or non-porous types, whether coated with collagen or un-coated, as described above. The ring 70 has a top portion shoulder 72 of generally annular shape and a central opening 73. A step wall 74 depends downwardly from the annular shoulder 72 and at the bottom end of the step wall is an outwardly extending is an circumferential flange 76. The valve body, illustratively shown by 80 and illustratively shown as being of disc shape, fits within the ring between the shoulder 72 and the flange 76. The height of the step wall 74 generally

corresponds to the height of the valve body 80. The opening 73 at the top of the ring can be reinforced, such as by stitching 77, so that the valve body can be firmly engaged.

To attach the heart valve body 80 to the heart, the body is placed within the ring 70 and oriented with the ring flange 76 positioned opposite the heart tissue. The surgeon then makes sutures through the flange 76 to the heart tissue. The valve body 80 will be firmly held relative to the heart between the flange 76 and the shoulder 72 with its reinforcement 77.

Once the valve body is attached, the inorganic antimicrobial agent of the suturing ring 70 fabric functions to kill bacteria from body parts and fluid that contact it. Thus, the suturing ring provides an added degree of protection against infection.

When the ring 70 is made of the porous fabric there is an advantage in that the porosity of the fabric allows fluid access to the valve body which maintains better temperature stability between the valve body and the heart.

Whether the fabric is porous or non-porous, it is preferred that the fabric forming the ring have the antimicrobial agent on both surfaces so that it also will be more active against bacteria and organisms between the ring and the heart valve body.

The ring 70 can be formed from the fabric by any suitable technique, such as cutting a piece of the fabric to size, making the opening 73, etc. Since the fabric 70 has the coating material 18, which can have shape retaining characteristics, some types of the fabric can be shaped by pressure or heat, or combination of the two, depending on the type of coating material. For example, if the fabric coating material 18 to which the agent is applied is an acrylic or other material with thermosetting properties, a slightly heated die can be used having the shape of ring 70. The heating is carried out at a level such as not to remove the coating material. If the fabric is to be heated to shape it into the ring, it is preferred that the collagen be applied after the heating.

The suturing ring 70 shown in Fig. 5 is only illustrative of the various types of rings that can be produced using the fabric of the invention which, as explained above, has the necessary antimicrobial properties as well as being able to

be easily formed in the shape shown as well as to permit its attachment to tissue by sutures. In all cases, the antimicrobial action of the fabric reduces the possibility of infection occurring at the valve implantation site.

In some cases a suturing ring is used with a heart valve body that is non-circular or in which it is desired to be able to position the suturing ring relative to the body. Various arrangements for doing this are shown in U.S. patent 5,766,240. One of the embodiments of that patent is shown in Figs. 6 and 6A adapted for using the novel inorganic antimicrobial fabric of the invention.

Referring to Figs. 6 and 6A, there is an annular collar 90 having upper and lower sections 91 and 93 between which is a depressed center section 92 which extends inwardly of sections 91 and 93. The collar center section 92 is to fit into a corresponding peripheral depression 82 in the outer wall of the valve body 80. Here the suturing ring 170 is formed by taking a piece of the fabric 170, laying it between the valve body groove 82 and the collar center section 92 which is press fit in the valve body groove 82. The fabric is played out to form a loose loop 174 of the fabric and the fabric ends are sewn at 176 to complete the ring. There are wraps of a cord 177 around the collar center section to prevent it from being damaged by a needle inadvertently making contact.

In using the arrangement of Figs. 6 and 6A, the collar 90 holds the fabric suturing ring 170 in position relative to the valve body and is rotatable about the valve body to position the ring 170, as desired. The surgeon can manipulate the loose hanging ring loop 174, such as by pulling part of it down, so that sutures can be made through the ring 170 to the heart tissue. The use of the antimicrobial fabric is particularly advantageous in this type of a suturing ring since body fluid can be present in the space between the collar and the inner part of the ring which could create infection problems. The antimicrobial action of the fabric acts to prevent this.

The antibiotic properties of the antibiotic zeolite particles of the invention may be assayed while in aqueous formulations using conventional assay techniques, including for example determining the minimum growth inhibitory concentration (MIC) with respect to a variety of bacteria, eumycetes and yeast. In such a test, the bacteria listed below may be employed:

Bacillus cereus var mycoides,  
Escherichia coli,  
Pseudomonas aeruginosa,  
Staphylococcus aureus,  
5 Streptococcus faecalis,  
Aspergillus niger,  
Aureobasidium pullulans,  
Chaetomium globosum,  
Gliocladium virens,  
10 Penicillium funiculosum,  
Candida albicans,  
Saccharomyces cerevisiae,

The assay for determining MIC can be carried out by smearing a solution containing bacteria for inoculation onto a plate culture medium to which a  
15 test sample of the encapsulated antibiotic zeolite particles is added in a particular concentration, followed by incubation and culturing of the plate. The MIC is defined as a minimum concentration thereof required for inhibiting the growth of each bacteria.

The present invention will hereunder be explained in more detail with  
20 reference to the following non-limiting working examples.

#### Example 1

A 1" x 1" sample of knitted polyester, available from Bard Vascular  
Systems Division as knitted polyester style no. 6103, was coated with an antibiotic  
25 hydrophilic coating as follows.

A coating solution containing 2.90% by weight of hydrophilic polyurethane available as Tecophilic™ from Thermedics; 96.81% tetrahydrofuran; and 0.29% AW-10N zeolite, available from Shinagawa, Inc., was prepared and  
mixed with a high shear mixer.

30 An eye dropper was used to apply the coating solution to the polyester sample. The polyester sample was then sprayed with air to remove excess powder and cure the coating.

### Example 2

A Dow Shaker Test was performed on the polyester sample prepared in Example 1 (hereafter referred to as Sample A) to determine its inhibitory effect against *S. aureus*. The Dow Shaker Test is based on Dow Corporate Test Method 0923 for testing aerobic bacteria by Dow Chemical. The Dow Shaker Test is described below.

Sample A was sterilized at 121 °C for 15 minutes.

A culture tube containing *S. aureus* was prepared by adding one disk of *S. aureus* to the culture tube. From about 2 to 5 ml of broth was added to the culture tube. Then the culture tube was agitated with a vortex mixer until the disk was completely dissolved in the broth. The bacteria in the culture tube was incubated for at least 3 hours at 35 °C. The culture tube was then refrigerated at about 2-8 °C until needed for testing.

A 5 ml sample of bacteria from the culture tube was removed and agitated in a vortex mixer. The absorbance of the sample was measured at 475 nm with a spectrophotometer relative to the absorbance of the aforementioned broth. Broth and/or bacteria from the culture tube were added to the sample until an absorbance of about 0.1 absorbance units was obtained. This corresponded to from about  $10^5$  to about  $10^6$  colony forming units per milliliter (CFU/ml).

5 ml of suspension was extracted from the sample and added to a flask containing 70 ml of sterile buffer. The resulting solution contained from about  $10^4$  to about  $10^5$  CFU/ml. The flask was capped and shaken on a wrist action shaker for 1 minute at maximum speed. This is referred to as time "0 hours" below.

The number of colony forming units in 1 ml of the solution was determined at time 0 hours by the following procedure. 1 ml of solution was extracted from the flask and added to a vial containing 9 ml of buffer solution to form a 10:1 dilution. The solution was repeatedly diluted with buffer solution until a plate count of about 30 to about 200 CFU/ml was obtained.

1 ml of the solution from the flask and each dilution were transferred to separate petri dishes. About 15-20 ml of molten agar was added to each dish. Each dish was rotated 10 times clockwise and 10 times counter-clockwise to



evenly distribute the agar and bacteria. Then, each dish was incubated for 18-24 hours at 35 °C. A plate count was performed on the petri dish containing from about 30 to about 200 bacteria colony forming units to determine the number of colony forming units.

Also, at time 0 hours, sample A was added to the flask and shaken with a wrist action shaker for 1 hour. The number of colony forming units in 1 ml of the solution in the flask was determined by the procedure above using 2 petri dishes. If the numbers of colony forming units in the 2 petri dishes were not within 15% of each other, the entire Dow Shaker Test was repeated.

The number of colony forming units in 1 ml of the solution was also determined after shaking the flask with a wrist action shaker for 18 and 24 hours.

A control was tested by the same procedure as sample A. The control was a 1" x 1" sample of knitted polyester, available from Bard Vascular Systems Division as knitted polyester style no. 6103.

The number of colony forming units at times 0 hours, 1 hour, 18 hours, and 24 hours for sample A and the control are in Table 1. The percentage of bacteria killed by sample A and the control at times 1 hour, 18 hours, and 24 hours are in Table 2.

Table 1

Sample	Bacteria Counts of <i>S. aureus</i> (Colony Forming Units)			
	0 hours	1 hour	18 hours	24 hours
Sample A	780,000	2,145,000	85,000	3,700
Control	480,000	12,400,00	4,720,00	4,300,000

Table 2

Sample	% Killed		
	1 hour	18 hours	24 hours
Sample A	0	89.10%	99.53%
Control	0	0	0

As indicated in Table 2, Sample A exhibited 99.53% inhibition of *S. aureus* after 24 hours of contact with the bacteria.

### Example 3

Safety and biocompatibility tests were conducted on the antibiotic zeolites employed in the invention. ISO 10993-1 procedures were employed. The following results were obtained:

<p>Cytotoxicity: <b>Non-Toxic</b></p> <p>Acute Systemic Toxicity: <b>Non-Toxic</b></p> <p>Intracutaneous Toxicity: <b>Passed</b></p> <p>Skin Irritation Test: <b>Non-Irritant</b></p> <p>Chronic Toxicity: <b>No Observable Effect</b></p> <p><i>In-vitro</i> Hemolysis: <b>Non-Hemolytic</b></p> <p>30-day Muscle Implant Test: <b>Passed</b></p> <p>60-day Muscle Implant Test: <b>Passed</b></p> <p>90-day Muscle Implant Test: <b>Passed</b></p> <p>Ames Mutagenicity Test: <b>Passed</b></p> <p>Pyrogenicity: <b>Non-Pyrogenic</b></p>
---

Thus, the antibiotic zeolites are exceptionally suitable under relevant toxicity and biocompatibility standards for use in the fabric.

**WE CLAIM:**

1                   1. An implantable heart valve having at least one heart valve  
2 mechanism, and a suturing ring of a fabric containing an inorganic antimicrobial  
3 agent to attach said valve body to heart tissue by passing sutures through said  
4 ring.

1                   2. An implantable heart valve as in claim 1 wherein said fabric is  
2 porous.

1                   3. An implantable heart valve as in claim 1 wherein said fabric is  
2 coated with collagen.

1                   4. An implantable heart valve as in claim 1 wherein said valve has a  
2 body with top and bottom surfaces and a wall there between, said suturing ring  
3 having an annular top part fitting over one of said top and bottom surfaces and  
4 defining an opening to said heart valve and a step wall depending from said  
5 annular top part to extend along said valve body wall.

1                   5. An implantable heart valve as in claim 4 wherein said suturing ring  
2 further comprises a flange ring extending outwardly from the end of said step wall  
3 opposite said annular top part.

1                   6. An implantable heart valve as in claim 1 wherein the fibers of said  
2 fabric are coated with a coating material having embedded particles of an inorganic  
3 antimicrobial agent, and said coating material is elastomeric.

1                   7. An implantable heart valve as in claim 6 wherein said coating  
2 material is selected from the group consisting of acrylic, polyurethane, silicone,  
3 latex, polyglycolic lactic acid, a biodegradable polymer, a hydrophilic biodegradable  
4 polymer, and a non-degrading polymer.

1                   8. An implantable heart valve as in claim 7 wherein said non-  
2 degrading polymer is a hydrophilic polyurethane.

1                   9. An implantable heart valve as in claim 1 wherein the fibers of said  
2 fabric are selected from the group consisting of cotton, nylon, polyester, Teflon, e-  
3 PTFE and blends of these materials.

1                   10. An implantable heart valve as in claim 1 wherein said  
2 antimicrobial agent is a metal.

1                   11. An implantable heart valve as in claim 1 wherein said  
2 antimicrobial agent is a zeolite.

1                   12. An implantable heart valve as in claim 6 wherein said  
2 agent is dispersed on the coating material in the quantity of between 0.5 and 20%,  
3 more preferably between 0.5 and 10% and most preferably between 1.5 and 5.0%  
4 of the matter that remains on the fabric, exclusive of the fabric.

1                   13. An implantable heart valve as in claim 12 wherein the particle  
2 size of said agent is between 0.8 and 10 microns.

1                   14. An implantable heart valve as in claim 6 wherein the fiber of said  
2 fabric is polyester, said coating material is a hydrophilic polymer and said agent is a  
3 zeolite.

1                   15. A suturing ring to attach the body of an implantable heart valve  
2 to body tissue comprising a ring of fabric having a portion to contact the valve  
3 body and a portion for accepting sutures to be fastened to the body tissue, said  
4 fabric containing an inorganic antimicrobial agent.

1                   16. A suturing ring as in claim 15 wherein said fabric is coated with  
2 collagen.

17. A suturing ring as in as in claim 15 wherein said fabric is porous.

18. A suturing ring as in claim 17 wherein said fabric is coated with collagen.





19. A suturing ring as in claim 15 wherein the fibers of said fabric piece are of a type having voids and said antimicrobial agent in said voids.

20. A suturing ring as in claim 15 wherein said fabric is non-porous and said antibiotic agent is over the entirety of said fabric.

21. A suturing ring as in claim 20 further comprising a coating of a tissue compatible material on said fabric.

22. A suturing ring as in claim 15 wherein the valve body has top and bottom surfaces and a wall there between, said suturing ring portion for contacting the body having an annular top part to fit over one of said top and bottom surfaces and defining an opening to said heart valve and a step wall depending from said annular top part to extend along said valve body wall.

23. A suturing ring as in claim 15 further comprises a flange ring extending outwardly from the end of said step wall opposite said annular top part.



2/2




FIG. 5




FIG. 5A

FIG. 6





FIG. 6A



THIS PAGE BLANK (USPTO)



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
2 June 2000 (02.06.2000)

PCT

(10) International Publication Number  
**WO 00/30567 A3**

(51) International Patent Classification<sup>7</sup>: A61F 2/24

(21) International Application Number: PCT/US99/27272

(22) International Filing Date:  
16 November 1999 (16.11.1999)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/197,808 23 November 1998 (23.11.1998) US

(71) Applicant: AGION TECHNOLOGIES, L.L.C.  
[US/US]; 60 Audubon Road, Wakefield, MA 01880  
(US).

(72) Inventors: HOLLEY, Steven; 24 Bigelow Street,  
Brighton, MA 02135 (US). BARRY, John, E.; 18 Drake  
Lane, Derry, NH 03038 (US). TROGOLO, Jeffrey, A.;  
228 Commonwealth Avenue, Boston, MA 02116 (US).

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ,  
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,  
DM, EE, ES, FI, GB, GD, GE, HR, HU, ID, IL, IN, IS, JP,

KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD,  
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,  
SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN,  
YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent  
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent  
(AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU,  
MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GW, ML, MR, NE, SN, TD, TG).


Published:  
— with international search report

(88) Date of publication of the international search report:  
18 October 2001

(15) Information about Correction:  
Previous Correction:  
see PCT Gazette No. 46/2000 of 16 November 2000, Sec-  
tion II

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: ANTIMICROBIAL SUTURING RING FOR HEART VALVE



(57) Abstract: A suturing ring to attach the body of an im-  
plantable heart valve to heart tissue by sutures is composed of  
a fabric containing an inorganic antimicrobial agent. The fab-  
ric can have a material coating the fibers of the fabric in which  
particles of the agent are embedded. The coating material can  
be elastomeric and the fabric porous, to improve its flexibility,  
or non-porous and the fabric ring can be coated with a tissue  
compatible substance such as collagen. One type of ring has  
an annular top part to fit over one of top and bottom surfaces  
of the valve body and defining an opening to the heart valve, a  
step wall depending from the annular top part to extend along  
said valve body wall and an outwardly extending flange through  
which the sutures are to be sewn.

WO 00/30567 A3

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 99/27272

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 A61F2/24

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 14139 A (ST JUDE MEDICAL) 9 April 1998 (1998-04-09)  figures 1-3 page 3, line 28 -page 5, line 31 page 7, line 32 -page 10, line 11 page 14, line 6 - line 29	1-5,9, 10, 15-19, 22,23
Y	---	6,20,21
Y	WO 96 30060 A (AORTECH EUROP LTD ;MCDAID EDWARD (GB); WRIGHT JAMES GORDON (GB)) 3 October 1996 (1996-10-03) figures 1-8 page 4, line 30 - line 36 page 5, line 1 -page 8, line 31 page 11, line 4 - line 21	6
A	---	15
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*C\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

11 April 2000

Date of mailing of the international search report

19/04/2000

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Mary, C

# INTERNATIONAL SEARCH REPORT

Int lional Application No

PCT/US 99/27272

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 674 280 A (DAIGLE KENNETH P ET AL) 7 October 1997 (1997-10-07) column 4, line 50 -column 5, line 4	20,21
A	-----	1
P,A	US 5 895 420 A (MIRSCH II M WILLIAM ET AL) 20 April 1999 (1999-04-20) column 5, line 19 - line 37 column 6, line 29 - line 41	1,6-13
A	----- US 4 775 585 A (HAGIWARA ZENJI ET AL) 4 October 1988 (1988-10-04) cited in the application the whole document -----	11,14

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/27272

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9814139 A	09-04-1998	US 5895419 A	20-04-1999
		AU 4604997 A	24-04-1998
		BR 9712169 A	31-08-1999
		CN 1231591 A	13-10-1999
		CZ 9901070 A	11-08-1999
		EP 0948297 A	13-10-1999
		PL 332498 A	13-09-1999
WO 9630060 A	03-10-1996	AU 712268 B	04-11-1999
		AU 5154496 A	16-10-1996
		BR 9607909 A	09-06-1998
		CA 2216639 A	03-10-1996
		EP 0817652 A	14-01-1998
		JP 11502734 T	09-03-1999
US 5674280 A	07-10-1997	US 5477864 A	26-12-1995
		US 5509933 A	23-04-1996
		US 5169597 A	08-12-1992
		AU 5219693 A	16-06-1994
		CA 2110779 A	08-06-1994
		EP 0601804 A	15-06-1994
		JP 6233811 A	23-08-1994
		US 5690670 A	25-11-1997
		US 5782910 A	21-07-1998
		US 5716400 A	10-02-1998
		US 5676632 A	14-10-1997
		US 5562730 A	08-10-1996
		US 5713947 A	03-02-1998
		US 5685306 A	11-11-1997
		US 5683442 A	04-11-1997
		US 5573401 A	12-11-1996
		US 5545227 A	13-08-1996
		AT 104865 T	15-05-1994
		AU 6827490 A	27-06-1991
		CA 2032875 A	22-06-1991
		DE 69008507 D	01-06-1994
		DE 69008507 T	18-08-1994
		DK 437079 T	30-05-1994
		EP 0437079 A	17-07-1991
		ES 2053126 T	16-07-1994
		JP 6073475 A	15-03-1994
		ZA 9010217 A	30-10-1991
US 5895420 A	20-04-1999	US 5728152 A	17-03-1998
		AU 6274996 A	30-12-1996
		BR 9608581 A	29-12-1998
		CA 2221734 A	19-12-1996
		EP 0831755 A	01-04-1998
		JP 11507279 T	29-06-1999
		WO 9640012 A	19-12-1996
US 4775585 A	04-10-1988	JP 1729959 C	29-01-1993
		JP 59133235 A	31-07-1984
		JP 63054013 B	26-10-1988
		AU 549375 B	23-01-1986
		CA 1253992 A	09-05-1989
		EP 0116865 A	29-08-1984
		US 4911899 A	27-03-1990

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/27272

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4775585 A		US 4911898 A	27-03-1990

THIS PAGE BLANK (USPTO)